

<b>DESCRIPTION</b>	<b>RONAN ACRYLIC CLEAR OVERCOAT</b> is a solvent based, fast-drying acrylic clear topcoat with UV-inhibitive additives that is specially formulated to provide long lasting protection over painted surfaces including signs, bulletins and sculptures. This coating resists yellowing, oxidation, checking and cracking. It is also ideal for renewing faded signs.
<b>PRECAUTIONS</b>	Acrylic Clear Overcoat is not to be used on raw wood, vinyl, gold leaf or any surface which will come into contact with solvents or harsh cleaning agents. Before using Acrylic Clear Overcoat, a patch test is highly recommended to 1) Determine if Acrylic Clear Overcoat will cause cracking or lifting 2) Test adhesion and 3) Determine whether clear will provide the desired finish (it is especially important to test for clarity over dark colors and whites).
<b>SURFACE PREPARATION</b>	All surfaces must be clean, free from loose or peeling paint, grease, oil, dirt, rust, mill scale and other contaminants. If this procedure is not observed, the drying and adhesion of any coating will be adversely affected.  <b>WARNING!</b> If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-42-LEAD or log on to <a href="http://www.epa.gov/lead">www.epa.gov/lead</a> .
<b>APPLICATION</b>	Follow surface preparation instructions. Stir thoroughly before use. May be brushed, rolled or sprayed.  BRUSH: With any good quality bristle brush.  ROLLER: A foam or short nap roller will give the best results. Roll in one direction, rewet, then cross roll.  SPRAY: Apply by airless spray, conventional compressed air or HVLP spray system. Consult spray gun manufacturer's guide for recommended fluid tip size and air pressure.
<b>THINNING</b>	Do not thin under normal conditions. Apply at full strength for maximum efficiency.
<b>CLEAN UP</b>	Mineral Spirits
<b>DRY TIMES</b>	At 70°F and 50% relative humidity, Acrylic Clear Overcoat will be dry to touch in 30 minutes to two (2) hours, depending on conditions. Wait two (2) hours to handle and 48 hours to recoat. Wait 48 hours for a full cure. Dry times may take longer in cooler and/or more humid conditions.

# TECHNICAL DATA SHEET—PAGE 2

## ACRYLIC CLEAR OVERCOAT

<b>APPLICATION CONDITIONS</b>	Minimum temperature: 50°F Maximum temperature: 95°F Maximum humidity: 90%
<b>FINISH</b>	Gloss (90 measured at 60°)
<b>WEIGHT PER GALLON</b>	7.3 lbs (approximate)
<b>SOLIDS %</b>	40% by weight (approximate)
<b>VISCOSITY</b>	60-62 KU at 75°F
<b>THEORETICAL COVERAGE</b>	Approximately 400 square feet at 4 mils wet
<b>SPREAD RATE</b>	642 square feet @ 1 mil dry
<b>FLASH POINT</b>	105°F
<b>PACKAGING</b>	US Gallon (128 fl oz), 4/case US Quart (32 fl oz), 6/case
<b>STORAGE TEMPERATURE</b>	Minimum: 40°F Maximum: 95°F
<b>SHELF LIFE</b>	Two (2) years
<b>VOC INFO</b>	Actual/Regulatory VOC (as packaged) will not exceed 500 grams/liter (4.2 lbs/gallon)
<b>CAUTIONS</b>	Read Safety Data Sheet and/or all warnings on the label before handling or using this product.
<b>PRODUCT WARRANTY</b>	All recommendations for the use of Ronan products are based on tests and experience believed to be reliable. It is the responsibility of the purchaser to determine the suitability of this product for its intended use. Since the methods of use, conditions of application and the application itself are beyond the manufacturer's and seller's control, product warranty is restricted to replacement of defective materials only. No other warranty, written or oral, is expressed or implied.
<b>REVISION DATE</b>	December 5, 2018